

Design of cyclometallated 5- π -delocalized donor-1,3-di(2-pyridyl)benzene platinum(II) complexes with second-order nonlinear optical properties.

Nicolò Baggi,^a Eleonora Garoni,^a Alessia Colombo,^{*a,b,c} Claudia Dragonetti,^{a,b,c} Stefania Righetto,^{a,b,c} Dominique Roberto,^{a,b,c} Julien Boixel,^d Véronique Guerchais,^{*d} and Simona Fantacci^{*c}

^aDip. di Chimica dell'Università degli Studi di Milano, ^bUdR di Milano dell'INSTM, ^cIstituto di Scienze e Tecnologie Molecolari del CNR, via Golgi, 19, I-20133 Milano, Italy; ^dInstitut des Sciences Chimiques de Rennes UMR 6226 CNRS-Université de Rennes 1, Campus de Beaulieu, 35042 Rennes Cedex, France; ^eComputational Laboratory for Hybrid/Organic Photovoltaics (CLHYO), CNR-ISTM, Via Elce di Sotto 8, I-06213, Perugia, Italy

Corresponding authors: alessia.colombo@unimi.it, veronique.guerchais@univ-rennes1.fr, simona@thch.unipg.it

Abstract

The effect on the second-order nonlinear optical properties of the nature of the π -delocalized moiety in the position 5 of a 1,3-di(2-pyridyl)benzene cyclometallated to a platinum(II) center was investigated. The influence of the substitution of a double bond with a triple bond as bridge between a triphenylamino group and the cyclometallated phenyl ring was studied and turned out to be negligible. Remarkably, the novel easily-prepared platinum(II) complex with a cyclometallated 5-styryl-1,3-di(2-pyridyl)benzene is characterized by a good second-order NLO response, as determined in solution by the EFISH technique; it is a good candidate for application in photonics.

Keywords: Second-order nonlinear optics; EFISH; cyclometallated platinum(II) complexes.

Introduction

Compounds with second-order nonlinear optical (NLO) properties are of increasing interest as building blocks for the preparation of materials with potential applications in optical communications, optical data processing and storage, or electro-optical devices [1-2]. Among them, coordination compounds are fascinating because they give additional flexibility, when compared to organic compounds, due to the presence of NLO-active charge-transfer transitions between the metal and the ligands, at relatively low energy and of high intensity, and tunable by the nature, oxidation state and coordination sphere of the metal center [3-11].

In particular, the second-order NLO activity of substituted phenylpyridines increases upon cyclometallation, an effect that has led to cyclometallated Ru(II) [12], Ir(III) [13-23] and Pt(II) [23-24] complexes characterized by interesting NLO properties. Platinum(II) compounds incorporating an N^N^C -cyclometallated 6-phenyl-2,2'-bipyridine constitutes another interesting NLO-active family [25-26]. Besides, it was reported that Pt(II) complexes with tridentate ligands based on a cyclometallated 1,3-di(2-pyridyl)benzene, which offer the metal ion an N^C^N coordination environment, are characterized by an enhanced NLO efficiency with respect to the corresponding N^N^N -coordinated terpyridine complexes, as measured by the Hyper-Rayleigh Scattering technique [27]. The good second-order nonlinear optical properties of various platinum(II) complexes with a cyclometallated 1,3-di(2-pyridyl)benzene have also been evidenced by the electric-field induced second harmonic generation (EFISH) technique [28]. In particular, the cyclometallated Pt(II) chloro complex of *trans*-5-(*p*-(*N,N*-diphenylamino)styryl)-1,3-di(2-pyridyl)benzene (Figure 1, **Pt-1**) is characterized by a good second-order NLO response [29].

These results prompted us to investigate by the EFISH technique the known Pt(II) complex bearing a cyclometallated 5-(*p*-(*N,N*-diphenylamino)phenylethynyl)-1,3-di(2-pyridyl)benzene (**Pt-2**), previously studied for its luminescence properties and application in OLEDs [30], in order to understand the effect on the NLO properties of the substitution of a double bond by a triple bond as bridge between triphenylamino moiety and the cyclometallated phenyl ring. Besides, to verify the NLO importance of the *p*-(*N,N*-diphenylamino) donor group on the styryl moiety, we prepared the simple novel platinum(II) complex bearing a *trans*-5-(styryl)-1,3-di(2-pyridyl)benzene (**Pt-3**).




Figure 1. Investigated cyclometallated Pt(II) complexes.

Material and methods

Synthesis

General comments

All solvents were dried by standard procedures: THF was freshly distilled from Na/benzophenone under nitrogen atmosphere; *N,N*-dimethylformamide (DMF) was dried over activated molecular sieves; triethylamine (Et₃N) was freshly distilled over KOH. All reagents were purchased from Sigma-Aldrich and were used without further purification. Reactions requiring anhydrous or oxygen-free conditions were performed under nitrogen. Thin layer chromatography (TLC) was carried out with pre-coated Merck F₂₅₄ silica gel plates. Flash chromatography (FC) was carried out with Macherey-Nagel silica gel 60 (230-400 mesh).

¹H and ¹³C spectra were recorded at 400 MHz on a Bruker AVANCE-400 instrument. Chemical shifts (δ) are expressed in ppm relative to internal Me₄Si as standard. Signals are abbreviated as s, singlet; bs, broad singlet; d, doublet; t, triplet; q, quartet; m, multiplet. Mass spectra were obtained with a FT-ICR Mass Spectrometer APEX II & Xmass software (Bruker Daltonics) - 4.7 Magnet and Autospec Fission Spectrometer (FAB ionization). Elemental analyses were performed using an Exeter Analytical E-440 analyser. UV-visible spectra were recorded for solutions of the compounds in dichloromethane, in 1 cm pathlength quartz cuvettes using a Biotek Instruments XS spectrometer.

EFISH measurements

EFISH measurements [31] were carried out at the Dipartimento di Chimica of the Università di Milano, in DMF solutions at a concentration of 10⁻³ M, with a non-


resonant incident wavelength of 1.907 μm , obtained by Raman-shifting the fundamental 1.064 μm wavelength produced by a Q-switched, mode-locked $\text{Nd}^{3+}:\text{YAG}$ laser manufactured by Atalaser. The apparatus used for EFISH measurements is a prototype made by SOPRA (France). The $\mu\beta_{\text{EFISH}}$ values reported are the mean values of 16 measurements performed on the same sample. The sign of $\mu\beta$ is determined by comparison with the solvent.

Dipole moments calculation

All the reported calculations were performed with Gaussian09 (G09) [32] without any symmetry constraints. The molecular geometry of **Pt-1**, **Pt-2** and **Pt-3** has been optimized in DMF solution by a Density Functional theory (DFT) approach using the B3LYP [33] exchange-correlation functional. For Pt a LANL2DZ basis set [34] along with the corresponding pseudopotentials have been used, while all the other atoms have been described with a 6-31G* basis set [35]. Ground state dipole moments of the Pt compounds have been computed in DMF solution. DMF solvation effects were included in the calculations by means of the conductor-like polarizable continuum model (C-PCM) as implemented in G09 [36].

Synthesis of the platinum (II) complexes

Diethyl 3,5-dibromobenzylphosphonate was prepared according to the literature [37] Stille couplings were performed following a reported procedure [38], using 2-(tri-*n*-butylstannyl)pyridine freshly prepared according to the literature [39]. Complexes **Pt-1** and **Pt-2**, previously studied for their luminescence properties, were prepared as reported by some of us [29-30]. The novel complex **Pt-3** was prepared as shown in Scheme 1 by reaction of K_2PtCl_4 with the new pro-ligand **L-3** obtained as follows.



Scheme 1. Reagents and conditions: (i) Diethyl 3,5-dibromobenzylphosphonate, *t*-BuOK, THF, Ar, 0°C, then rt, 15 h; (ii) 2-(tri-*n*-butylstannyl)pyridine, LiCl, $\text{PdCl}_2(\text{PPh}_3)_2$, toluene, 110°C, 48 h; (iii) K_2PtCl_4 , AcOH, 118°C, 48 h.

1: Diethyl 3,5-dibromobenzylphosphonate (698 mg, 1.8 mmol) and benzaldehyde (230 mg, 2.1 mmol) were dissolved in THF (20mL) under Ar atmosphere at 0°C. *t*-BuOK (808 mg, 72 mmol) was added in small portions to the solution over 20 minutes, keeping the mixture under stirring. The mixture was then allowed to warm gradually at room temperature and stirred overnight. Afterwards, H₂O was added causing the formation of a precipitate and the mixture was stirred for 30 minutes. The solvent was partially removed under reduced pressure, the residue was extracted into CH₂Cl₂, the organic layer was dried over MgSO₄ and the solvent removed under reduced pressure. The crude product was purified by flash chromatography (silica, hexane:CH₂Cl₂, 7:3). The pure compound was obtained as a yellow solid (412 mg). Yield: 58%. ¹H-NMR (400 MHz, CDCl₃) δ (ppm): 7.56 (2H, d, *J* = 1.6 Hz), 7.53 (1H, t, *J* = 1.7 Hz), 6.49 (2H, d, *J* = 8.0 Hz), 7.38 (2H, t, *J* = 7.8 Hz), 7.30 (1H, m), 7.09 (1H, d, *J* = 16.2 Hz), 6.92 (1H, d, *J* = 16.2 Hz). ¹³C-NMR (101 MHz, CDCl₃) δ (ppm): 141.0, 136.3, 132.6, 131.5, 128.8, 128.4, 128.8, 126.8, 125.6, 123.2.

L-3. A mixture of the bromo derivative (410 mg, 1.06 mmol), 2-(tri-*n*-butylstannyl)pyridine (858 mg, 2.33 mmol), PdCl₂(PPh₃)₂ (37 mg, 0.05 mmol) and LiCl (360 mg, 8.48 mmol) were suspended in toluene (10 mL) and heated at reflux under argon atmosphere for 48 h. After cooling to room temperature, an aqueous solution of NaOH 1 M was added. The resulting solution was extracted with AcOEt and the organic layer was dried over MgSO₄ and the solvent removed under reduced pressure. The crude product was purified by flash chromatography (silica, petroleum ether/Et₂O, 1:1). The desired product was obtained as a white solid (160 mg). Yield: 45%. ¹H NMR (400 MHz, CD₂Cl₂) δ (ppm): 8.76 (2H, d, *J* = 4.2 Hz), 8.51 (1H, s), 8.26 (2H, s), 7.89 (2H, d, *J* = 7.8 Hz), 7.80 (2H, t, *J* = 7.6 Hz), 7.58 (2H, d, *J* = 7.4 Hz), 7.40, (2H, t, *J* = 7.5 Hz), 7.29 (5H, m). ¹³C-NMR (101 MHz, CD₂Cl₂) δ (ppm): 157.1, 149.7, 140.3, 138.5, 137.3, 136.8, 129.6, 128.8, 128.4, 127.8, 126.6, 125.7, 124.7, 122.4, 120.8. Elem. Anal. calcd for C₂₄H₁₈N₂: C, 86.20; H, 5.43; N, 8.38. Found: C, 84.30; H, 5.45; N, 7.99.

Pt-3. The pro-ligand L-3 (100 mg, 0.3 mmol) was dissolved in acetic acid (5 ml). The solution was degassed through freeze-pump-thaw cycles. K₂PtCl₄ (149 mg, 0.36 mmol) was added and the mixture was heated at reflux for 2 days. A yellow precipitate formed: it was filtered, washed with MeOH, H₂O, EtOH and Et₂O and dried under vacuum to obtain pure **Pt-3** as a yellow powder (130 mg). Yield: 77%. ¹H NMR (400 MHz, CD₂Cl₂) δ (ppm): 9.33 (2H,

dt, $J = 16.1$ Hz, 6.6 Hz), 8.05 (2H, t, $J = 7.7$ Hz), 7.71 (2H, s), 7.62 (2H, d, $J = 7.9$ Hz), 7.36 (8H, m), 7.21 (1H, d, $J = 16.2$ Hz). Elem. Anal. calcd for $C_{24}H_{17}ClN_2Pt$: C, 51.12; H, 3.04; N, 4.97. Found: C, 51.34; H, 3.05; N, 4.95. MS (FAB⁺), calculated: ($C_{24}H_{17}N_2Pt$): m/z 528.10 [M-Cl]. Found: m/z 528 [M-Cl].

Results and Discussion

The investigated platinum(II) complexes (Figure 1) are readily prepared by reaction of K_2PtCl_4 with the related 5- π -delocalized donor-1,3-di(2-pyridyl)benzene pro-ligand dissolved in acetic acid (see Material and methods).

The main absorption bands in the UV-visible spectra, carried out in CH_2Cl_2 at 298 K, are given in Table 1. Like other platinum(II) complexes with a cyclometallated 1,3-di(2-pyridyl)benzene, **Pt-3** shows a strong band at 263 nm, which can be assigned to intraligand $^1\pi-\pi^*$ transitions of the cyclometallated 1,3-di(2-pyridyl)benzene, and a less-intense absorption band at 421 nm in agreement with transitions of mixed charge-transfer/ligand-centered character [28].

Table 1. Main absorption bands in the UV-visible spectra, dipole moments and second-order NLO response.

	Absorption ^a λ_{max} / nm ($\epsilon / M^{-1} cm^{-1}$)	$\mu\beta_{EFISH}^b$ ($\times 10^{-48}$ esu)	μ^c (D)	β_{EFISH} ($\times 10^{-30}$ esu)
Pt-1 ^d	295 (21000), 378 (15700), 430sh (4900)	-880	10.7	-82
Pt-2	240 (35 100), 292 (27100), 338sh (18 200), 363 (22800), 416sh (6380)	-764	11.0	-69
Pt-3	263 (9441), 421 (2364)	-660	9.5	-69

(a) In CH_2Cl_2 . (b) in DMF at 1.907 μm ; estimated uncertainty in EFISH measurements is $\pm 10\%$. (c) computed dipole moments in DMF solution using B3LYP//6-31g*/LANL2DZ// C-PCM level of theory. (d) from reference 29.

The quadratic hyperpolarizability of the three complexes was measured by the solution phase direct current EFISH generation method, which can provide direct information on the intrinsic molecular NLO properties through eq 1:

$$\gamma_{EFISH} = (\mu\beta_i/5kT) + \gamma(-2\omega; \omega, \omega, 0) \quad (1)$$

where $\mu\beta_\lambda/5kT$ is the dipolar orientational contribution and $\gamma(-2\omega; \omega, \omega, 0)$ is the third-order polarizability corresponding to the mixing of two optical fields at ω and the dc poling field at $\omega=0$. This latter term is often referred as the electronic cubic contribution to γ_{EFISH} , which is usually negligible. β_λ is the projection along the dipole moment (μ) axis of the vectorial component of the tensor of the quadratic hyperpolarizability at the incident wavelength λ . All EFISH measurements were carried out working in CH_2Cl_2 solutions at a concentration of 10^{-3} M, with a non resonant incident wavelength of 1.907 μm , obtained by Raman-shifting in a high pressure H_2 of the fundamental 1.064 μm wavelength produced by a Q-switched, mode-locked Nd^{3+} :YAG laser.

All complexes are characterized by a negative value of $\mu\beta_{\text{EFISH}}$ (Table 1), as determined by the EFISH technique working in DMF solution. This negative sign is in agreement with a decrease of the excited state dipole moment with respect to the ground state [40], suggesting that the second-order dipolar NLO response is dominated by the charge transfer from platinum to the cyclometallated ligand [28-29]. In order to obtain the β_{EFISH} values, we calculated the dipole moments in DMF solution. Complexes **Pt-1** and **Pt-2** are characterized by a similar dipole moment, a bit higher than that of **Pt-3** which lacks the triphenylamino moiety. The β_{EFISH} value of **Pt-1** is quite similar to that of **Pt-2**, showing that the substitution of a double bond by a triple bond, as bridge between the triphenyl amino moiety and the cyclometallated ring (Figure 1), has a negligible NLO influence in this kind of complexes. It turned out that the easily-prepared novel complex **Pt-3** is characterized by a similar β_{EFISH} value. This observation indicates that it is not necessary to have a donor substituent on the styryl group in order to reach a high second-order NLO response. Besides, it is worth pointing out that all the complexes investigated here are characterized by better $\mu\beta_{\text{EFISH}}$ values, due to better β_{EFISH} values, than the platinum(II) complex bearing a cyclometallated 5-methyl-1,3-di(2-pyridyl)benzene ($\mu\beta_{\text{EFISH}} = -480 \times 10^{-48}$ esu; $\beta_{\text{EFISH}} = -47 \times 10^{-30}$ esu) [28].

Conclusion

In conclusion, our work gives some indications for the design of 5- π -delocalized donor-1,3-di(2-pyridyl)benzene platinum(II) complexes with interesting second-order nonlinear optical properties. Remarkably, the simple platinum complex bearing a cyclometallated 5-styryl-1,3-di(2-pyridyl)benzene shows a good quadratic hyperpolarizability and has a great potential for application in photonics.

Acknowledgements

This work was supported by MIUR and CNR in Italy. Regione Lombardia and Fondazione Cariplo are gratefully acknowledged for the use of instrumentation purchased through the SmartMatLab Centre project (2014). We thank CNRS for a financial support (PICS Rennes-Milan) and l'Università Italo Francese (Progetto Galileo 2015/2016; G15_50) for mobility support.

References

- [1] N. P. Prasad, D. J. Williams, In *Introduction to Nonlinear Optical Effects in molecules and Polymers*; Wiley, 1991.
- [2] J. Zyss, *Molecular Nonlinear Optics: Materials, Physics and Devices*, Academic Press, Boston, 1994.
- [3] B. J. Coe, *Acc. Chem. Res.* 39 (2006) 383-393.
- [4] E. Cariati, M. Pizzotti, D. Roberto, F. Tessore, R. Ugo, *Coord. Chem. Rev.* 250 (2006) 1210-1233
- [5] J. P. Morrall, G. T. Dalton, M.G.Humphrey, M. Samoc, *Adv. Organomet. Chem.* 55 (2007) 61-136.
- [6] S. Di Bella, C. Dragonetti, M. Pizzotti, D. Roberto, F. Tessore, R. Ugo in *Topics in Organometallic Chemistry 28. Molecular Organometallic Materials for Optics*, Vol. 28 (Eds: H. Le Bozec, V. Guerchais), Springer, 2010, 1-55.
- [7] O. Maury, H. Le Bozec, in *Molecular Materials*; D.W. Bruce, D. O'Hare and R.I. Walton, Eds.; Wiley: Chichester, 2010, 1-59.
- [8] O. Maury, H. Le Bozec, *Acc. Chem. Res.* 38 (2005) 691-704.
- [9] F. Tessore, D. Roberto, R. Ugo, P. Mussini, S. Quici, I. Ledoux-Rak, J. Zyss, *Angew. Chem. Intern. Ed.* 42 (2003) 456.
- [10] I.P. Oliveri, S. Failla, A. Colombo, C. Dragonetti, S. Righetto, S. Di Bella, *Dalton Trans.*, 43 (2014) 2168
- [11] M.G. Humphrey, T. Schwich, P.J. West, M.P. Cifuentes, M. Samoc, In *Comprehensive Inorganic Chemistry II (Second Edition): From Elements to Applications*, Elsevier: Oxford, U.K. 2013; Vol 8.
- [12] L. Labat, J.F. Lamere, I. Sasaki, P.G. Lacroix, L. Vendier, I. Asselberghs, J. Perez-Moreno, K. Clays, *Eur. J. Inorg. Chem.* 15 (2006) 3105.

- [13] C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, A. Valore, S. Fantacci, A. Sgamellotti, F. De Angelis, *Chem. Commun.* 40 (2007) 4116.
- [14] C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, A. Valore, F. Demartin, F. De Angelis, A. Sgamellotti, S. Fantacci, *Inorg. Chim. Acta* 361 (2008) 4070.
- [15] C. Dragonetti, S. Righetto, D. Roberto, A. Valore, T. Benincori, F. Sannicolò, F. De Angelis, S. Fantacci, *J. Mat. Sci.: Mat. Electr.* 20 (2009) S460.
- [16] C. Dragonetti, S. Righetto, D. Roberto, A. Valore, *Phys. Status Solid C* 6 (2009) S50.
- [17] A. Valore, E. Cariati, C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, F. De Angelis, S. Fantacci, A. Sgamellotti, A. Macchioni, D. Zuccaccia, *Chem. Eur. J.* 16 (2010) 4814.
- [18] V. Aubert, L. Ordroneau, M. Escadeillas, J.A.G. Williams, A. Boucekkine, E. Coulaud, C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, A. Valore, A. Singh, J. Zyss, I. Ledoux-Rak, H. Le Bozec, V. Guerchais, *Inorg. Chem.* 50 (2011) 5027.
- [19] C. Dragonetti, A. Valore, A. Colombo, S. Righetto, G. Rampinini, F. Colombo, L. Rocchigiani, A. Macchioni, *Inorg. Chim. Acta* 382 (2012) 72.
- [20] M. Zaarour, V. Guerchais, H. Le Bozec, C. Dragonetti, S. Righetto, D. Roberto, F. De Angelis, S. Fantacci, M.G. Lobello, *Dalton Trans.* 42 (2013) 155.
- [21] M. Zaarour, A. Singh, C. Latouche, J.A.G. Williams, I. Ledoux-Rak, J. Zyss, A. Boucekkine, H. Le Bozec, V. Guerchais, C. Dragonetti, A. Colombo, D. Roberto, A. Valore, *Inorg. Chem.* 52 (2013) 7987.
- [22] C. Dragonetti, A. Colombo, D. Marinotto, S. Righetto, D. Roberto, A. Valore, M. Escadeillas, V. Guerchais, H. Le Bozec, A. Boucekkine, C. Latouche, *J. Organomet. Chem.* 751 (2014) 568.
- [23] A. Valore, A. Colombo, C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, F. De Angelis, S. Fantacci, *Chem. Commun.* 46 (2010) 2414.
- [24] A. Colombo, C. Dragonetti, D. Marinotto, S. Righetto, D. Roberto, S. Tavazzi, M. Escadeillas, V. Guerchais, H. Le Bozec, A. Boucekkine, C. Latouche, *Organometallics* 32 (2013) 3890.
- [25] J. Boixel, V. Guerchais, H. Le Bozec, D. Jacquemin, A. Amar, A. Boucekkine, A. Colombo, C. Dragonetti, D. Marinotto, D. Roberto, S. Righetto, R. De Angelis, *J. Am. Chem. Soc.* 136 (2014) 5367.
- [26] J. Boixel, V. Guerchais, H. Le Bozec, A. Chantzis, D. Jacquemin, A. Colombo, C. Dragonetti, D. Marinotto, D. Roberto, *Chem. Commun.* 51 (2015) 7805.
- [27] A. Scarpaci, C. Monnereau, N. Hergué, E. Blart, S. Legoupy, F. Odobel, A. Gorfo, J. Pérez-Moreno, K. Clays, I. Asselberghs, *Dalton Trans.* (2009) 4538.

- [28] E. Rossi, A. Colombo, C. Dragonetti, S. Righetto, D. Roberto, R. Ugo, A. Valore, J. A. G. Williams, M. G. Lobello, F. De Angelis, S. Fantacci, I. Ledoux-Rak, A. Singh, J. Zyss, *Chem. Eur. J.* 19 (2013) 9875-9883.
- [29] F. Nisic, E. Cariati, A. Colombo, C. Dragonetti, S. Fantacci, E. Garoni, E. Lucenti, S. Righetto, D. Roberto, J. A. G. Williams, *Dalton Trans.* 46 (2017) 1179-1185.
- [30] F. Nisic, A. Colombo, C. Dragonetti, D. Roberto, A. Valore, J. M. Malicka, M. Cocchi, G. R. Freeman, J.A.G. Williams, *J. Mater. Chem. C* 2 (2014) 1791-1800.
- [31] (a) B. F. Levine, C. G. Bethea, *Appl. Phys. Lett.* 24 (1974) 445. (b) B. F. Levine, C. G. Bethea, *J. Chem. Phys.* 63 (1975) 2666. (c) I. Ledoux, J. Zyss, *Chem. Phys.* 73 (1982) 203.
- [32] M. J. Frisch, G. W. Trucks, H. B. Schlegel, G. E. Scuseria, M. A. Robb, J. R. Cheeseman, G. Scalmani, V. Barone, B. Mennucci, G. A. Petersson, H. Nakatsuji, M. Caricato, X. Li, H. P. Hratchian, A. F. Izmaylov, J. Bloino, G. Zheng, J. L. Sonnenberg, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J. Hasegawa, M. Ishida, T. Nakajima, Y. Honda, O. Kitao, H. Nakai, T. Vreven, J. A. Montgomery Jr., J. E. Peralta, F. Ogliaro, M. Bearpark, J. J. Heyd, E. Brothers, K. N. Kudin, V. N. Staroverov, R. Kobayashi, J. Normand, K. Raghavachari, A. Rendell, J. C. Burant, S. S. Iyengar, J. Tomasi, M. Cossi, N. Rega, J. M. Millam, M. Klene, J. E. Knox, J. B. Cross, V. Bakken, C. Adamo, J. Jaramillo, R. Gomperts, R. E. Stratmann, O. Yazyev, A. J. Austin, R. Cammi, C. Pomelli, J. W. Ochterski, R. L. Martin, K. Morokuma, V. G. Zakrzewski, G. A. Voth, P. Salvador, J. J. Dannenberg, S. Dapprich, A. D. Daniels, Ö. Farkas, J. B. Foresman, J. V. Ortiz, J. Cioslowski, D. J. Fox, *Gaussian 09, Revision D.01*, Gaussian, Inc., Wallingford CT, 2009.
- [33] (a) A. D. Becke, *J. Chem. Phys.* 98 (1993) 5648-5652. (b) C. Lee, W. Yang, R. G. Parr, *Phys. Rev. B: Condens. Matter* 37 (1988) 785-789. (c) B. Miehlich, A. Savin, H. Stoll, H. Preuss, *Chem. Phys. Lett.* 157 (1989) 200-206.
- [34] P. J. Hay, W. R. Wadt, *J. Chem. Phys.* 82 (1985) 299-310.
- [35] G. A. Petersson, M. A. Al-Laham, *J. Chem. Phys.* 94 (1991) 6081-6101.
- [36] (a) S. Miertus, E. Scrocco, J. Tomasi, *Chem. Phys.* 55 (1981) 117-129; (b) M. Cossi, V. Barone, R. Cammi, J. Tomasi, *Chem. Phys. Lett.* 255 (1996) 327-335.
- [37] E. Diez-Barra, J. C. Garcia-Martinez, S. Merino, R. Del Rey, J. Rodriguez-Lopez, P. Sanchez-Verdu, J. Tejeda, *J. Org. Chem.* 66 (2001) 5664-5670.
- [38] X.-S. Xiao, W. Lu, C.-M. Che, *Chem. Sci.* 5 (2014) 2482-2488.
- [39] T. N. Y Hoang, M. Humbert-Droz, T. Dutronc, L. Gueñée, C. Besnard, C. Piguet, *Inorg. Chem.* 52 (2013) 5570-5580.

[40] D. R. Kanis, P. G. Lacroix, M. A. Ratner, T. J. Marks, *J. Am. Chem. Soc.* 116 (1994) 10089-10102.